

## SHREE GANPATI CHEMICAL & MINERALS

Manufacturer & Exporter Gypsum, Pop,lime, Fly Ash Gypsum, Ball Clay, China Clay, Slica Send & More Minerals.

## IN HOUSE TESTING REPORT

**Product Name: -** Analysis Report of Quick Lime (87.5%)

**Testing Date: -**08 July 2020

Test Report No. : - SGCM/1005/20-21



| Sr. No. | Specification   | Unit   | Test Results | Slaking           | time ratio      |
|---------|---|--------|--------------|-------------------|-----------------|
|         |   |        |              | +Powder Water 1:4 |                 |
| 1.      | Appearance  | Visual | White of     | Times in          | Temperature (C) |
|         |   |        |              | Minutes           |                 |
| 2.      | Available Lime As CAO   | %      | 69.96        | Qat Start         | 20.07           |
| 3.      | Available Lime As CA(OH) <sub>2</sub>                           | %      | N.A.         | 5                 | 30.75           |
| 4.      | Acid Insoluble (sio <sub>2</sub> )R <sub>2</sub> O <sub>2</sub> | %      | 1.80         | 10                | 36.65           |
| 5.      | Moisture as free water  | %      | N.A.         | 15                | 39.15           |
| 6.      | Magnesium as MGO  | %      | 2.72         | 20                | 46.05           |
| 7.      | $R_2O_3A_5(AI_2O_1+Fe_2O_2)$                                    | %      | N.A.         | 25                | 51.75           |
| 8.      | Aluminum Oxide AS(AL <sub>2</sub> O <sub>3</sub> )              | %      | N.A.         | 30                | 53.15           |
| 9.      | Particle Size (mesh)100Bss                                      | %      | 98.85        | 35                | -               |
| 10.     | Residue +100 Bss  | %      | 1.25         | 40                | -               |
| 11.     | LOI (Loss of Ignition )   | %      | 6.15         | -                 | -               |

## Method of slaking reactivity of Quick Lime: -

Take 150gm Quick lime Powder of 100 Mesh & 600ml water at 20+0.7 input of slaking, note the time & Temperature ratio.

- Note: 1. Lime tested as per ISI 1514 Sugar Method Percentage by Mass.
  - 2. The Above reports has been tested on request of concern party.
  - 3. No Liability accepted for in disputes cases arising in joint testing /results Due to it is hygroscopic minerals etc.



🖷 A-144, Ansal Sushant City, Jaislmer Road, Bikaner (Raj.) **№ 20 KHM, BALLAR ROAD, DANTOR, BIKANER (RAJASTHAN)**